



Q- Increase or Q- slope ?


(medium field)

Origin of dissipations


Theory vs Experiment

P. Dhakal, et al., PR
A. Grassellino, et al.,
26(10): p. 102001.

JLab



FNAL



1

BROOKHAVEN
NATIONAL LABORATORY




Jefferson Lab 09/23/13


Courtesy C. Reece/ B.P. Xiao

Courtesy A. Grasselino

Saclay
1999
 $Q_0 \sim 6.10^{11}$





Fashion week... New 2013 model





Point Contact Tunneling

FNAL Cavity Samples:
 1) 205A Nitrogen treated
 2) C8 Cold Spot High Field Q slope



Δ Sup. Gap
 Γ DOS Broadening
 Z Barrier Strength
 Tunneling to Ohmic


Nb Single Crystal (110) Processed
 Standard EP, de-ionized water
 Air dry (C. Antoine)



Contrast

High Q consistent with:


- Near ideal BCS Gap, $\Gamma/\Delta < 5\%$
- High Z oxide barrier
- No de-pairing



Depairing Γ coming from oxide/interface


Temperature dependent medium field Q-slope

The Interface Tunnel Exchange (ITE) Model



- Surface electric field only penetrates the oxides not the superconductor
- Exchange of electrons within one RF period yields an electric surface resistance proportional to f
- Within the energy gap 2Δ there are no states available → Threshold effect


Temperature independent medium field Q-slope



To explain this data set with magnetic losses one would need a model, which assumes $R_s(B)$ prop. to f^3 .

In the Quadrupole Resonator the ratio between E/B is proportional to f . Therefore the data can be explained by a model assuming $R_s(E)$ prop to f after subtracting low field losses

Temperature independent medium field Q-slope



In the Quadrupole Resonator the ratio between E/B is proportional to f . Therefore the data can be explained by a model assuming $R_s(E)$ prop to f after subtracting low field losses



Origin of medium field losses

The new study leading to the deconvolution in $R_{BCS}(B)$ and $R_0(B)$ [1] allows to draw some important new conclusions on the origin of the low and medium field RF losses:


1. Both residual resistance and BCS resistance contribute to MFQS
2. Thermal feedback plays almost no role in avg performing 1.3 GHz cavities (below lambda point)
3. Roughness plays a role: BCP causes more MFQS than EP (manifests as residual)
4. 120C bake enhances the MFQS by making the BCS component strongly field dependent
5. Reverse field dependence is possible! Impurity doping leads to a BCS resistance decreasing with field, reaching BCS values previously unseen in our niobium

[1] A. Romanenko and A. Grassellino, Appl. Phys. Lett. **102**, 252603 (2013)

Origin of low and medium field losses – BCS component



1. EP, BCP: clean limit →
 - High low field value bc of large mfp
 - No Q-slope bc of no $\Delta(H)$
2. 120C bake: dirty limit →
 - Lower low field value bc of low mfp
 - Strong field dependence bc of $\Delta(H)$ (bc of dirty limit)
3. Nitrogen baked: Intermediate purity →
 - Lower low field value bc of low mfp
 - Decrease bc of $\lambda(B)$? Or is nitrogen a better dopant?



Origin of low and medium field losses – residual part

1. Hydrides:

- Low field: yes (hydrides always present as shown via cryogenic TEM by Trenikhina and Romanenko, residual consistently <1 nΩ in annealed as last step cavities demonstrated at FNAL)
- Field dependence: yes (see second cooldown $R_s(B)$)

2. (Macro)Roughness (BCP vs EP):


- Low field: no
- Field dependence: yes

3. Trapped flux:


- Low field: yes
- Field dependence: yes, linear

4. Oxide and suboxides:



- Low field: maybe (increase in 120C localized in first ~ 3 nm)
- Field dependence: not clear




Trapped flux produces a linear field dependence [$R_0(B)$]



Benvenuti, Calatroni et al, Proceedings of the 1997 Workshop on RF Superconductivity, Abano Terme (Padova), Italy






Hydrogen affects the field dependence of residual resistance: example second cooldown



Knobloch and Padamsee, 8th Workshop on RF Superconductivity, Padova, Italy. SRF 981012-12



M. Checchin and A. Grassellino, to be published






Temperature dependent medium field Q-slope

Quadrupole Resonator measurements on one bulk niobium sample



All curves can be fitted by $Rs(T,B) = Rs(T) \cdot c \cdot (B/B_c)^2$ with $c=10.2+/-2.5$ independent on T and f


Temperature independent medium field Q-slope



To explain this data set with magnetic losses one would need a model, which assumes $R_s(B)$ prop. to f^3 .

In the Quadrupole Resonator the ratio between E/B is proportional to f . Therefore the data can be explained by a model assuming $R_s(E)$ prop to f after subtracting low field losses

Temperature independent medium field Q-slope




In the Quadrupole Resonator the ratio between E/B is proportional to f . Therefore the data can be explained by a model assuming $R_s(E)$ prop to f after subtracting low field losses

Temperature independent medium field Q-slope

ITE fit can explain cavity data

Example: Early HIE Isolde QWR measurement (100 MHz)



Summary on medium field Q-slope

Combined results of surface resistance measurements on samples and cavities allow to conclude:

1. There are temperature dependent and independent contributors to the medium field Q-slope.
2. The temperature dependent surface resistance factorizes in a temperature and a field dependent part like $Rs(T,B)=Rs(T)\cdot c \cdot (B/B_c)^2$, where c is a constant independent of T and f . These losses can be correlated to the surface magnetic field.
3. Often a surface resistance increasing above a threshold field, saturating at higher field is observed. Quadrupole Resonator measurements give evidence that these losses are caused by the surface electric field and the interface tunnel exchange model can provide a good fit to the data with physically meaningful parameters.



Dissipation Mechanisms in SRF Cavities from Tunneling and Raman Spectroscopies

J. Zasadzinski

Illinois Institute of Technology/ Argonne Lab

Principal Collaborators:

IIT: C. Cao, M. Warren, A. Korczakowski
Argonne: T. Proslier, N. Groll, D. Ford
UIC: R. Tao, R. Klie (TEM/EELS)

Nb Samples: SRF (Hot Spot, Cold Spot), Processed Nb Coupons

FNAL: L. Cooley, A. Romanenko, A. Grassellino
Jlab: G. Ciovati
CEA: C. Antoine



No Singular Theme: Multimodal Processes

- Nb Oxide is NOT a benign dielectric (defective, variable conductivity, variable barrier strength, locally magnetic, source of De-Pairing)
- Hot Spots/ Cold Spots differ in the area density of macroscopic surface blemishes (etch pits, rough pits, patches of excess C, O, H)
- Very Best regions show ideal Nb gap, ideal oxide/interface, no depairing
- Surprises: NbC inclusions (50 nm - 1 μm) (Raman/TEM/EELS)

Point Contact Tunneling

FNAL Cavity Samples:
 1) 205A Nitrogen treated
 2) C8 Cold Spot High Field Q slope



Similar Results - Near Ideal BCS



High Q consistent with:



- Near ideal BCS Gap, $\Gamma/\Delta < 5\%$
- High Z oxide barrier
- No de-pairing

Grassellino et al, 2013
Supercond. Sci. Technol. 26 102001



Δ Sup. Gap
 Γ DOS Broadening
 Z Barrier Strength
 Tunneling to Ohmic

Nb Single Crystal (110) Processed Standard EP, de-ionized water Air dry (C. Antoine)




$\Gamma/\Delta > 20\%$

Contrast




Depairing Γ coming from oxide/interface

Δ Gap
 Γ DOS Broadening
 Z Barrier Strength



Tunneling in Cavity Hot Spots



Hot Spots show distribution of Gaps as low as 1.0 meV.


Important $R_S \sim e^{-\Delta/kT}$

Areas of reduced T_C

Origin? NbH_x , NbC_x , Proximity Effects, magnetism?

Need new probes! Measure local gap, composition, structure

Spin flip tunneling (zero bias peak)




Hot spots show regions of Kondo tunneling - magnetic moments in the oxide!


Is the origin of Pairbreaking Γ Magnetic moments in oxide?

Raman/SEM Mapping of Surface Blemishes


Jlab Hot Spot




Amorphous C



FNAL 205A




Chain Hydrocarbons CH₂



C. Cao et al,
PhysRevSTAB.16.064701

SEM probes 1 μm
Thick excess C
Excess O also



Summary of Surface Blemish Studies:

- Higher density of blemishes on Hot Spots
- Raman shows a-C, CH₂ chains, NbC (inclusions in TEM)
- SEM shows excess carbon can be thick
- Raman not sensitive to NbH_x need FTIR?
- Is excess C tied to reduced gaps in hot spots?